

Product Data Sheet

Edition 8.1.2008
 Identification no. 481
 Sikaflex-11 FC

Sikaflex®-11 FC

One part advanced polyurethane,
 elastomeric sealant/adhesive

Description	Sikaflex-11 FC is a one-component, gun-grade, adhesive and sealing compound of permanent elasticity. This dual-purpose material is based on a special moisture-cured polyurethane with an accelerated curing time.
Where to Use	<p>As an elastic adhesive for:</p> <ul style="list-style-type: none"> ■ Cover plates, gaskets and coverings. ■ Acoustic ceiling tiles. ■ Floor moldings and door sills. ■ Light weight construction materials. ■ Wood, metal, or plastic window and door frames. ■ Roof tiles. <p>As an elastic joint sealer for:</p> <ul style="list-style-type: none"> ■ Air ducts and high vacuum systems. ■ Containers, tanks, and silos. ■ Gaskets in openings in walls or floors for ducts, piling, etc. ■ Reservoirs or water retaining structures. ■ Aluminum fabrication. ■ Bolted lap joints.
Advantages	<ul style="list-style-type: none"> ■ Excellent adhesion on all cement-based materials, brick, ceramics, glass, metals, wood, epoxy, polyester, acrylic resin, and plastics. ■ Fast cure rate. ■ Good weathering and water resistance. ■ Non-corrosive. ■ Can be painted over with water, oil, and rubber-based paints. (Preliminary tests recommended). ■ High durability.
Coverage	10.1 fl. oz. cartridge seals 12.4 lineal ft. of 1/2 x 1/4 in. joint.
Packaging	Disposable 10.1 fl. oz., moisture-proof composite cartridges, 12/case.

Typical Data (Material and curing conditions @ 73°F and 50% R.H.)

Shelf Life	9 months in unopened container.
Storage Conditions	Store at 40°-95°F (4°-35°C). Condition material to 65°-75°F before using.
Color	White
Application Temperature	40° to 100°F. Sealant should be installed when joint is at mid-range of its anticipated movement.
Service Range	-40° to 170°F
Curing Rate	Tack-free Time (TT-S-00230C) 1 to 2 hours depending on climate. Final Cure 5 to 8 days
Recovery	ASTM C-719 >90%
Shore A Hardness (ASTM D-2240)	40-45
Tensile Properties (ASTM D-412)	Tensile Stress 225 psi Elongation at Break 600%
Lap-Shear Strength (ASTM D-1002) modified, glass substrate	73 F/50% RH 165 psi
Weathering Resistance	Excellent
Chemical Resistance	Good resistance to water, weak acids, weak alkalis, sewerage, mineral oils, vegetable oils, fats, fuels,. (Not resistant to organic solvents, paint thinner, strong acids, strong alkalis). Consult Technical Service for specific data.

How to Use

Surface Preparation Clean all surfaces. Joint walls must be sound, clean, dry, frost-free, and free of oil and grease. Curing compound residues and any other foreign matter must be thoroughly removed.



Priming

Priming is not usually necessary for anodized aluminum, steel, non-absorbent materials such as glass, ceramics, stoneware and tiles. Most substrates only require priming if testing indicates a need or where sealant will be subjected to water immersion after cure. Consult Technical Service for additional information on priming.

Application

Recommended application temperatures: 40°-100°F. For cold weather application, condition material to 65°-75°F before using.

Place nozzle of gun into bottom of the joint and fill entire joint. Keep the nozzle in the sealant; continue on with a steady flow of sealant preceding the nozzle to avoid air entrapment. Avoid overlapping of sealant to eliminate entrapment of air. Tool as required. Joint dimension should allow for 1/4 inch minimum and 1/2 inch maximum thickness for sealant. Proper design is 2:1 width to depth ratio.

Storage

Store in dry warehouse conditions between 40°F and 80°F. Shelf life under these conditions is 9 months.

Limitations

- Allow 3-day cure at standard conditions when using Sikaflex-11 FC in total water immersion situations and prior to painting.
- Avoid exposure to high levels of chlorine. (Maximum level is 5ppm).
- Maximum depth of sealant must not exceed 1/2 in.; minimum depth is 1/4 in.
- Maximum expansion and contraction should not exceed 12.5% of average joint width.
- Avoid contact with alcohol and other solvent cleaners during cure.
- Do not apply when moisture-vapor-transmission condition exists from the substrate as this can cause bubbling within the sealant.
- Use opened cartridges the same day.
- When applying sealant, avoid air-entrapment.
- Since system is moisture-cured, permit sufficient exposure to air.
- White color tends to yellow slightly when exposed to ultraviolet rays.
- The ultimate performance of Sikaflex-11 FC depends on proper application, good design and proper preparation of joint surfaces.
- Not for use in expansion joints.
- Heavier substrates may require additional support during the cure period.

Caution

Combustible: Keep away from open flames and high heat. Contains xylene; avoid breathing vapors. Use with adequate ventilation.

Irritant; Sensitizer - Contains polyisocyanate prepolymer, xylene. Avoid breathing vapors. Use with adequate ventilation. May cause skin/eye/respiratory irritation. May cause skin and/or respiratory sensitization after prolonged or repeated contact. Avoid contact. Overexposure to xylene may cause headaches, dizziness or other CNS effects. Use only with adequate ventilation. Use of safety goggles and chemical resistant gloves is recommended. If PELs are exceeded, use an appropriate, properly fitted NIOSH approved respirator. Remove contaminated clothing.

First Aid

In case of skin contact, wash immediately and thoroughly with soap and water. If symptoms persist, consult physician. For eye contact, flush immediately with plenty of water for at least 15 minutes; contact physician. For respiratory problems, remove person to fresh air; if symptoms persist, contact a physician. In case of ingestion, dilute with water and consult physician. Remove contaminated clothing.

Clean Up

In case of spills or leaks, wear suitable protective equipment, contain spill, collect with absorbent material, and transfer to suitable container. Ventilate area. Avoid contact. Dispose of in accordance with current, applicable local, state, and federal regulations.

In case of emergency, call **CHEMTREC** 1-800-424-9300

Linear Feet of Sealant per Gallon

Inches	Depth					
	1/4	1/2	3/4	1	1 1/4	1 1/2
1/4	308.0					
1/2	154.0	77.0				
3/4	102.7	51.3	34.2			
1	77.0	38.5	25.7	19.3		
1 1/4	61.6	30.8	20.5	15.4	12.3	
1 1/2	51.3	25.7	17.1	12.8	10.3	8.6

Width

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at www.sikacorp.com or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at www.sikaconstruction.com or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.

LIMITED WARRANTY: Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKASHALL NOT BELIEVABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKASHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at www.sikaconstruction.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Sika and Sikaflex are registered trademarks. Made in USA. Printed in Canada.

